

TEST REPORTREPORT NO. : TS-061248
DATE : JAN. 02, 2007
PAGE : 1 of 3APPLICANT: BEAUTIFUL WINDOW ENTERPRISE CO., LTD.
NO. 382, YUAN-LU RD., SEC. 1,
FUHSING, CHANGHUA 506,
TAIWAN, R.O.C.TEL: (886) 4-7787996, EXT. 1213
FAX: (886) 4-7789867
ATTN: MS. HUANG**SAMPLE DESCRIPTION PROVIDED BY APPLICANT:**ITEM DESCRIPTION : 2" FAUX WOOD BLIND -A: 2" PRINTED SLAT 23"X48" SAND (451T)
2" FAUX WOOD BLIND -B: 2" UN-PRINTED SLAT 23"X48" SAND (451T)
PO NUMBER : NO INFORMATION
STYLE NUMBER : NO INFORMATION
COLOR : SAND - 451T
COUNTY OF DISTRIBUTION : U.S.A.
DATE OF SAMPLE RECEIVED : DEC. 26, 2006
TESTING PERIOD : DEC. 26, 2006 - JAN 02, 2007
PLACE OF TESTING : TAIWAN**TESTS CONDUCTED:** AS PER APPLICANT'S REQUEST.**TESTS REQUIRED AND RESULT:** PLEASE REFER TO THE FOLLOWING PAGES FOR DETAILS.

TEST PARAMETER	CONCLUSION
FLAME TEST (NFPA 701: 1999), TEST METHOD 2	PASS

REMARK: THE RESULT RELATES ONLY TO THE ITEMS TESTED.

PREPARED AND CHECKED BY

INGRED HUANG
TECHNICAL MANAGER

Copyright of this report is owned by the Specialized Technology Resources (Taiwan) Ltd. and may not be reproduced other than in full except with the written approval of the issuing Company.

See Reverse For Terms And Conditions Of Service

SPECIALIZED TECHNOLOGY RESOURCES (TAIWAN) LTD.

7/F., No. 150, Jian-Yi Road, Zhonghe City, Taipei County, Taiwan, R.O.C. Tel.: (02) 8226-3298 Fax.: (02) 8226-3098

LETTERS & REPORTS : Specialized Technology Resources (Taiwan) Ltd., letters and reports are issued for the exclusive use of the clients to whom they are addressed. No quotations from reports or use of the Specialized Technology Resources (Taiwan) Ltd., name is permitted except as expressly authorized in writing. Letters and reports apply only to the specific materials, products or processes tested, examined or surveyed and are not necessarily indicative of the qualities of apparently identical or similar materials, products or processes. The liability of Specialized Technology Resources (Taiwan) Ltd., with respect to services rendered shall be limited to the amount of consideration paid for such services and not include any consequential damages.

TEST REPORTREPORT NO. : TS-061248
DATE : JAN. 02, 2007
PAGE : 2 of 3**SUMMARY OF TEST RESULTS****FIRE TESTS (NFPA 701-1999):
TEST METHOD 2****PERFORMAMNCE CRITERIA:**

1. When any specimen continues flaming for more than 2 seconds after the test flame is removed from contact with the specimen, the material shall be recorded as having failed the test. **AFTERFLAME: ≤ 2 seconds**
2. When the char length of any single specimen exceeds 435 mm (17.1 in.), the material shall be recorded as having failed the test. **CHAR LENGTH: <435 mm**
3. When at any time during or after the application of the test flame any portions or residues of the material being tested break or drip from the specimen and fall to the floor of the test apparatus and continue burning for more than 2 seconds after reaching the floor of the test apparatus, the material shall be recorded as having failed the test. **DRIP BURN: ≤ 2 seconds**

TEST RESULTS: PASS

SAMPLE: 2" FAUX WOOD BLIND – A: 2" PRINTED SLAT 23"X48" SAND (451T)

SAMPLE NO.	AFTER FLAME (seconds)	CHAR LENGTH (mm)	DRIP BURN (seconds)
1	0	280	0
2	0	275	0
3	0	260	0
4	0	255	0
5	0	260	0
6	0	275	0
7	0	270	0
8	0	275	0
9	0	280	0
10	0	270	0

***** End of Page *****

Copyright of this report is owned by the Specialized Technology Resources (Taiwan) Ltd. and may not be reproduced other than in full except with the written approval of the issuing Company.

See Reverse For Terms And Conditions Of Service

SPECIALIZED TECHNOLOGY RESOURCES (TAIWAN) LTD.

7/F., No. 150, Jian-Yi Road, Zhonghe City, Taipei County, Taiwan, R.O.C. Tel.: (02) 8226-3298 Fax.: (02) 8226-3098

LETTERS & REPORTS : Specialized Technology Resources (Taiwan) Ltd., letters and reports are issued for the exclusive use of the clients to whom they are addressed. No quotations from reports or use of the Specialized Technology Resources (Taiwan) Ltd., name is permitted except as expressly authorized in writing. Letters and reports apply only to the specific materials, products or processes tested, examined or surveyed and are not necessarily indicative of the qualities of apparently identical or similar materials, products or processes. The liability of Specialized Technology Resources (Taiwan) Ltd., with respect to services rendered shall be limited to the amount of consideration paid for such services and not include any consequential damages.


TEST REPORT

TEST RESULTS: PASS


SAMPLE: 2" FAUX WOOD BLIND – B: 2" UN-PRINTED SLAT 23"X48" SAND (451T)

SAMPLE NO.	AFTER FLAME (seconds)	CHAR LENGTH (mm)	DRIP BURN (seconds)
1	0	250	0
2	0	250	0
3	0	260	0
4	0	260	0
5	0	270	0
6	0	265	0
7	0	240	0
8	0	255	0
9	0	260	0
10	0	270	0

PRODUCT PHOTO:



SAMPLE A



SAMPLE B

***** End of Report *****

Copyright of this report is owned by the Specialized Technology Resources (Taiwan) Ltd. and may not be reproduced other than in full except with the written approval of the issuing Company.
 See Reverse For Terms And Conditions Of Service

SPECIALIZED TECHNOLOGY RESOURCES (TAIWAN) LTD.

7/F., No. 150, Jian-Yi Road, Zhonghe City, Taipei County, Taiwan, R.O.C. Tel.: (02) 8226-3298 Fax: (02) 8226-3098

LETTERS & REPORTS : Specialized Technology Resources (Taiwan) Ltd., letters and reports are issued for the exclusive use of the clients to whom they are addressed. No quotations from reports or use of the Specialized Technology Resources (Taiwan) Ltd., name is permitted except as expressly authorized in writing. Letters and reports apply only to the specific materials, products or processes tested, examined or surveyed and are not necessarily indicative of the qualities of apparently identical or similar materials, products or processes. The liability of Specialized Technology Resources (Taiwan) Ltd., with respect to services rendered shall be limited to the amount of consideration paid for such services and not include any consequential damages.